

3 Rubber Sheeting

03TPSH.. HYPALON SHEET Polymer CSM

Use


Excellent resistance to ageing, ozone, weathering, heat, abrasion and cutting. Good resistance to medium and low concentration oxidising chemicals. Excellent mechanical characteristics.

Color: Black

Surface: smooth/smooth

Work Temperature:

Min. -35°C Max 140°C



GENERAL CHARACTERISTICS

Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
Modearte	Good	Good	Very Good	Good	Very Good

CHARACTERISTICS	UNIT OF MEASUREMENT	VALUE	TOLERANCE
Hardness	Sh.A	70	± 5
Elongation	%	225	
Specific weight	g/cm ³	1,40	

THICKNESS mm	HEIGHT mt	LENGTH mt
1	1,4	10
1,5	1,4	10
2/2,5	1,4	10
from 3 at 10	1,4	10
from 12 at 20	1,4	5
from 25 at 50	1	1